


AMENDMENTS TO THE CLAIMS


This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of claims

1. (withdrawn)
2. (currently amended) A support material consisting essentially of a cross-linked polymer compound in a three-dimensional network, comprising a radical of general formula (I) or (II):



where X represents an oxygen atom or the group -NH, m is an integer other than zero equal at most to 5, R represents a hydrogen atom or a substituted or non-substituted, linear or branched alkyl radical having from 1 to 8 carbon atoms, Y represents a single bond, -NH-CO-group, -NH-CS-group or -CO-group, A represents a single bond, a linear or branched alkylene radical having from 1 to 21 carbon atoms, an arylene radical having from 6 to 18 carbon atoms or an aralkylene radical having from 7 to 40 carbon atoms, L represents a bis-thioether radical, of general formula (IIIa), bis-sulphoxide radical of general formula (IIIb), or bis-sulphone radical, of general formula (IIIc), or a bis-silane radical of general formula (IV), below:




where S represents a sulphur atom, O an oxygen atom and Si a silicon atom and where -W₁ and W₃, identical or different, each represent:

a linear or branched alkylene radical having from 1 to 21 carbon atoms, an arylene radical having from 6 to 18 carbon atoms, or an aralkylene radical having from 7 to 40 carbon atoms;

W₂ represents a single bond, W₁ an oxygen atom, a sulphur atom or a symmetrical diester of formula



R₅ represents a linear or branched alkyl radical having from 1 to 5 carbon atoms or hydrogen, and R₄ represents the radical



where R₆ is (CH₂)_{n2} or oxygen and where n₁ varies from 0 to 3000 and n₂ from 0 to 10, the arylene radicals contained respectively in the radicals of general formulae (I) and (II) being able to be substituted by one or more atoms or radicals, identical or different, of at least one halogen atom, at least one alkyl radical containing from 1 to 4 carbon atoms, at least one alkoxy radical containing from 1 to 4 carbon atoms or at least one nitro group.



3. (original) A support material according to claim 2, wherein the support material is in the form of a ball.
4. (original) A support material according to claim 2, wherein the support material contains a percentage of less than 80%.
5. (original) A support material according to claim 4, wherein the support material is obtained from a mineral or an organic porous support.
6. (withdrawn) A method of preparing a support material according to claim 2 and containing essentially a cross-linked polymer compound, wherein a polysaccharide or oligosaccharide derivative is dissolved in an organic polar solvent then precipitated in the form of at least one ball, the ball is then cross-linked in situ, wherein the ball consists essentially of the cross-linked polymer compound.
7. (withdrawn) A method of preparing a support material according to claim 3 in the form of a precipitated ball, wherein a polysaccharide or an oligosaccharide derivative is dissolved in a polar organic solvent and that the organic solution obtained is poured onto an aqueous solution containing an anionic surfactant and an emulsion stabilizer and that the emulsion obtained is heated in order to eliminate the organic solvent.
8. (withdrawn) A method of preparing according to claim 7, wherein the polar organic solvent is mesityl oxide, the anionic surfactant is sodium dodecyl sulphate and the emulsion stabilizer is a polyhydroxylated derivative possessing a number of carbon atoms greater than 16.
9. (withdrawn) A method of preparing according to claim 7, wherein the ball has a dimension of 0.1-300 μ m and a specific surface area of 10-100 m²/g.
10. (withdrawn) A method of preparing according to claim 7, wherein the precipitated

ball of a polysaccharide derivative is cross-linked in situ, so that the cross-linked polymer compound obtained in the form of a ball constituting a support material which is insoluble in a polar organic solvent, and the ball of support material has a dimension of 0.1-300 μ m and a specific surface area of 10-100 m²/g.

11. (withdrawn) A method of preparing a support material according to claim 4, comprising adding a solution of an organic solvent containing the polysaccharide or oligosaccharide derivative to a powdery commercial porous support, heating the medium in order to evaporate the solvent, suspending the powder obtained and containing the polysaccharide or oligosaccharide derivative in a solvent in which the compounds are insoluble and refluxing the medium; adding a cross-linking agent after reaction, and filtering and washing the suspension in a polar organic solvent in which the polysaccharide or oligosaccharide derivatives are soluble in order to eliminate these later.


12. (withdrawn) A process for preparing and separating enantiomers by employing means of liquid, gaseous or supercritical chromatography using polar organic solvents, comprising exposing enantiomers to a support material according to claim 2.

13. (currently amended) A percolation membrane comprising a cross-linked polymer compound in a three-dimensional network, comprising a radical of general formula (I) or (II):



where X represents an oxygen atom or the group -NH, m is an integer other than zero equal at most to 5, R represents a hydrogen atom or a substituted or non-substituted, linear or branched alkyl radical having from 1 to 8 carbon atoms, Y

represents a single bond, -NH-CO-group, -NH-CS-group or -CO-group, A represents a single bond, a linear or branched alkylene radical having from 1 to 21 carbon atoms, an arylene radical having from 6 to 18 carbon atoms or an aralkylene radical having from 7 to 40 carbon atoms, L represents a bis-thioether radical, of general formula (IIIa), bis-sulphoxide radical of general formula (IIIb), or bis-sulphone radical, of general formula (IIIc), or a bis-silane radical of general formula (IV), below:



where S represents a sulphur atom, O an oxygen atom and Si a silicon atom and where -W₁ and W₃, identical or different, each represent:

a linear or branched alkylene radical having from 1 to 21 carbon atoms, an arylene radical having from 6 to 18 carbon atoms, or an aralkylene radical having from 7 to 40 carbon atoms;

W₂ represents a single bond, W₁ an oxygen atom, a sulphur atom or a symmetrical diester of formula




R₅ represents a linear or branched alkyl radical having from 1 to 5 carbon atoms or hydrogen, and R₄ represents the radical



where R_6 is $(CH_2)_{n_2}$ or oxygen and where n_1 varies from 0 to 3000 and n_2 from 0 to 10, the arylene radicals contained respectively in the radicals of general formulae (I) and (II) being able to be substituted by one or more atoms or radicals, identical or different, of at least one halogen atom, at least one alkyl radical containing from 1 to 4 carbon atoms, at least one alkoxy radical containing from 1 to 4 carbon atoms or at least one nitro group.

14. (withdrawn) A process of organic synthesis in a heterogeneous phase comprising a support material according to claim 2.

15. (currently amended) A support material according to ~~claim 4~~ claim 2, wherein the radical of general formulae (I) or (II) is bound to at least one an osidic chiral unit of a linear, branched or cyclic linkage of a polysaccharide or oligosaccharide derivative according to the general formulae (VII) and (VIII):



where X, Y, A, R, L each have the same meaning as defined in claim 1 and the chiral unit represents an osidic chiral unit of a linear, branched or cyclic linkage of a polysaccharide or oligosaccharide derivative, it being understood that wherein "chain i"

and "chain j" ~~symbolize the fact that the~~ represent chiral units at each end of the radicals of formulae (I) and (II) are situated as separate chains or separate linkages of osidic units, within the polysaccharide or oligosaccharide.

16. (new) A support material according to claim 2, wherein L corresponds to formula (IIIa).

17. (new) A support material according to claim 2, wherein L corresponds to formula (IIIb).

18. (new) A support material according to claim 2, wherein L corresponds to formula (IIIc).

19. (new) A support material according to claim 2, wherein L corresponds to formula (IV).